Non-Metallic Systems

Korifit Coupler



| _ | | | | | 4 | | |
|---|----|-----|---------|------|-----|---------|---|
| | hn | บกว | 1 (: r | nara | cta | ristics | • |
| | | | | 1010 | CLG | | |

Conforms to BSI Kitemark KM-35161

Low voltage directive

Approvals and Standards

High Impact Resistance Degree of mechanical protection

IP65 - As standard Degree of protection

UV protection High

Straight one piece coupler- White (W) only Fitting Characteristics

For coupling two corrugated flexible conduits Application

Application Min Temp Max Temp Normal operating temperature range

> Static - 5°C +60°C Dynamic - 5°C +60 °C

Korifit type KFL lightweight, KFS standard weight & KFM medium weight For use with - Conduit Series

Test Standard Performance Rating Fire performance

> Not Rated Not Rated

Click or See page 3 Testing data

Polyamide (Nylon) 66 Type of material

Image



The Company's policy is one of continuous improvement and reserves the right to change specifications at any time without prior notice.


Non-Metallic Systems

Korifit Coupler



Dimensional Data

| Part No | No | Weight in grams | | |
|----------|------|-----------------|------|--------|
| T dit NO | A | В | С | (Each) |
| KF2020 | 66.0 | 24.5 | 28.0 | 13.5 |



The Company's policy is one of continuous improvement and reserves the right to change specifications at any time without prior notice.

Technical Data Sheet 201408 Page 3

Non-Metallic Systems

Korifit Coupler



BS EN 61386 Classification

| | Fitting | Compression | Impact | Min temp | Max temp | bending | electrical | IP solids | IP water | Corrosion | Tensile | Non-flame Propogating | Suspended load |
|--|---------|-------------|--------|-------------|-------------|---------|------------|--------------|-------------|-----------|---------|--------------------------|-------------------|
| | AL | N/A | 2 | 2 | 1 | N/A | 2 | 6 | 5 | 0 | 1 | 1 | 0 |

Mechanical Properties

| Test Type | Methods / Standards | Requirements | Value |
|------------------------|---------------------|--|---------|
| Tensile Strength | IEC61386-1 | 2 mins at Specified Value (KF Conduit) | Class 1 |
| Tensile Strength | | Ultimate Pullout (KF Conduit) | 220N |
| Impact Strength @ -5°C | IEC61386-1 | No visible damage | Class 2 |

Tensile Tests to IEC 61386 gives the minimum classification value only. Actual values will depend on the type and size of the fittings used and will always be greater than the minimum – Impact strength is the minimum classification value at the minimum temperature – actual values will depend on size and temperature. Specific values available on request.

Thermal Properties

| Test Type | Methods / Standards | Requirements | Value |
|------------------------|---------------------|------------------------------|---------------|
| Static Short Term Temp | | Temporary Use (3000hrs) | -5°C to +60°C |
| Static Long Term Temp | | Permanent Use (30,000) Hours | -5°C to +60°C |

Chemical Resistance Chart

| | Astm No.1 | Diesel oil | Methyl Bromide | | Sulphur Dioxide (Gas) |
|----------------------|----------------------|-------------------------|------------------------|--------------|-----------------------|
| | Astm No.2 | Diethylamine | MEK | | Sulphuric Acid (10%) |
| Key: | Astm No.3 | Ethanol | Nitric Acid (10%) | \subset | Sulphuric Acid (70%) |
| | Acetic Acid (10%) | Ether | Nitric Acid (70%) | | Toluene |
| Suitable : | Acetone | Ethylamine | Oxalic Acid | \mathbb{C} | Transformer Oil |
| | Aluminium Chloride | Ethylene Glycol | Ozone (Gas) | | 1,1,1-Trichloroethane |
| Limited Suitability: | Aniline | Ethyl Ethanoate | Paraffin oil | | Trichloroethylene |
| _ | Benzaldehyde | Freon 32 | Petrol | | Turpentine |
| Unsuitable : | Benzene | Hydrochloric Acid (10%) | Phenol | | Vegetable Oil |
| | Carbon tetrachloride | Hydrochloric Acid (36%) | Sea Water | | Vinyl Acetate |
| Not Tested : | Chlorine water | Hydrogen Peroxide (35%) | Silver Nitrate | | Water |
| | Chloroform | Hydrogen Peroxide (87%) | Skydrol | | White Spirit |
| | Citric Acid | Lactic Acid | Sodium Chloride | | Zinc Chloride |
| | Copper Sulphate | Lubricating oil | Sodium Hydroxide (10%) | | |
| | Cresol | Methanol | Sodium Hydroxide (60%) | | |

The information above is given as a guide only and is based on published technical data and experience. The chemical resistance of the above products is dependant on factors such as chemical exposure, concentration of the chemical and temperature. The above chemicals are valid for a temperature of 23°C. Use of the above table is at the users own discretion and risk. Those using it must satisfy themselves that their application presents no health and safety risks. The end user should assess compatibility with their application and contact Thomas & Betts for further information.

ADHERENCE TO THE CURRENT WIRING REGULATIONS BS7671 OR NEC WIRING REGULATIONS (FOR USA) IS STRONGLY ADVISED.

MINIMUM BEND RADIUS FOR FLEXING IS DEPENDANT UPON MINIMUM TEMPERATURE, BENDING FREQUENCY AND CHEMICAL ENVIRONMENT.

The Company's policy is one of continuous improvement and reserves the right to change specifications at any time without prior notice.

CMG House - Station Road - Coleshill - B46 1HT - United Kingdom

Tel: +44(0)1675 468 222 - Fax: +44(0)1675 464 930

Technical Support e-mail: cmg.conduitsystems@abb.com - www.adaptaflex.co.uk